

FOXAPOX-GL (OX-520 GL) Polyamide Epoxy

PRODUCT DESCRIPTION	A gloss high build polyamide cured epoxy coating.
RECOMMENDED USE	Suitable for use in both maintenance and new construction situations as part of an anti-corrosive coating system and protect steel and concrete surfaces against alkaline, salt and solvent solution.
CHARACTERISTICS	<ul style="list-style-type: none"> Good resistance to splash, spillage and fumes of alkaline, salt and solvent solution. Hard and abrasion resistance. Resist continuous immersion in alkaline (up to 50% concentration) at ambient temperature. Resist continuous immersion in petroleum products such as motor fuels, jet fuels, diesel oil and gasoline. Resist continuous immersion in salt solution, fresh or demineralised water.
PHYSICAL DATA	<p>Colour Available On Request</p> <p>Gloss level Gloss</p> <p>Volume</p> <p>Solid Approx. 70%</p> <p>Dry Film</p> <p>Thickness 125 microns per coat</p> <p>Number of Coat 2 – 3</p> <p>Theoretical Coverage 5,60 sq.m/ for 125 microns</p> <p>Temperature</p> <p>Resistance Maximum : 93⁰C (dry)</p> <p>VOC 313 g/</p> <p>Flash Point Base : 24⁰C Hardener : 40⁰C</p> <p>Shelf Life At least 12 months</p> <p>Pack Size</p> <p>20 Kgs unit Base : 16 Kgs , Hardener : 4 Kgs</p>
SURFACE PREPARATION	Dry abrasive blast in accordance with ISO – Sa 2.5 or SSPC – SP 10 “Near White”. Remove abrasive residue or dust from surface..
APPLICATION DATA	<p>Application Methods</p> <p>Airless</p> <p>Spray</p> <p>Nozzle Tip</p> <p>Nozzle Pressure</p> <p>Conventional Spray</p> <p>Nozzle Tip</p> <p>Approx. 0.46 mm (0.018 inch)</p> <p>10 MPa (approx. 1400 psi)</p> <p>Approx. 1.8 mm (0.071 inch)</p>

Nozzle Pressure	0.3 MPa (approx. 43 psi)
Brush or Roller	Can be applied by brush or roller but may require several coats to achieve the same film thickness
Mixing Ratio By Volume	Base : Hardener = 4 : 1
Thinner	FOXANER 005
Surface Temperature	Should be $10^0\text{C} - 49^0\text{C}$, at least 3^0C above the dew point to prevent condensation
Drying Time	
Touch Dry	2 hours at 25^0C , 1 hour at 32^0C
Through Dry	14 hours at 25^0C , 7 hours at 32^0C
Recoat Time	10 hours at 25^0C , 5 hours at 32^0C
Curing Time	9 days (under ventilated conditions)
Pot Life	8 hours at 25^0C , 4 hours at 32^0C

SAFETY PRECAUTION

Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against topic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

DISCLAIMER

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.

ISSUED: **January 2010**