

DATA SHEET

MIL-PRF-22191, TY 2, CL 2

Structure: Poly/Mylar

Barrier Material: Meets all requirements of MIL-PRF-22191, TY 2, CL 2 and is intended for packaging of O-rings, metal parts, and other materials requiring minimal moisture protection.

Properties	Typical Value	Unit of Measure	Test Method
Tensile Strength: MD	18	Lbs. at break	ASTM D882
XMD	17		
Tear Strength: MD	50	grams	ASTM 689
XMD	50		
Burst	50	psi	Mullen
MVTR	3	g/100 sq in/24 hrs	Mocon
Caliper	3	mils	

Disclaimer: The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.

P.O. Box 36216 • Pensacola, Florida 32516 • P 850.898.3797 • F 901.276.0294 • sales@midsouthpackaging.com

