

FOXAPOX-GL (OX-501 GL)

Polyamide Epoxy

PRODUCT DESCRIPTION	A gloss high build polyamide cured epoxy coating.	
RECOMMENDED USE	Suitable for use in both maintenance and new construction situations as part of an anti-corrosive coating system and protect steel and concrete surfaces against alkaline, salt and solvent solution.	
CHARACTERISTICS	• Good resistance to splash, spillage and fumes of alkaline, salt and solvent solution. • Hard and abrasion resistance. • Resist continuous immersion in alkaline (up to 50% concentration) at ambient temperature. • Resist continuous immersion in petroleum products such as motor fuels, jet fuels, diesel oil and gasoline. • Resist continuous immersion in salt solution, fresh or demineralised water up to 60⁰C.	
PHYSICAL DATA	Colour	Available On Request
	Gloss level	
	Volume Solid	
	Dry Film Thickness	125 microns per coat
	Number of Coat	
	Theoretical Coverage	4.40 sq.m/l for 125 microns
	Temperature Resistance	: 93 ⁰ C (dry)
	VOC	
	Flash Point	: 24 ⁰ C
		: 40 ⁰ C

Shelf Life	At least 12 months
Pack Size	
20 Kgs unit	Base : 16 Kgs , Hardener : 4 Kgs

SURFACE PREPARATION

Dry abrasive blast in accordance with ISO – Sa 2.5 or SSPC – SP 10 “Near White”. Remove abrasive residue or dust from surface..

APPLICATION DATA

Application Methods

Airless Spray	
Nozzle Tip	Approx. 0.46 mm (0.018 inch)
Nozzle Pressure	10 MPa (approx. 1400 psi)
Conventional Spray	
Nozzle Tip	Approx. 1.8 mm (0.071 inch)
Nozzle Pressure	0.3 MPa (approx. 43 psi)
Brush or Roller	Can be applied by brush or roller but may require several coats to achieve the same

Mixing Ratio By Volume Thinner

Base : Hardener = 4 : 1
FOXANER 005

Surface Temperature

Should be 10⁰C – 49⁰C, at least 3⁰C above the dew point to prevent condensation

Drying Time

Touch Dry	2 hours at 25 ⁰ C, 1 hour at 32 ⁰ C
Through Dry	14 hours at 25 ⁰ C, 7 hours at 32 ⁰ C
Recoat Time	10 hours at 25 ⁰ C, 5 hours at 32 ⁰ C
Curing Time	9 days (under ventilated conditions)

Pot Life

8 hours at 25⁰C, 4 hours at 32⁰C

SAFETY PRECAUTION

Keep away from heat, spark and Open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use.

Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building.

DISCLAIMER

The information in this product data sheet is given to the best of our knowledge based on laboratory testing and practical experience. If the product is used under condition beyond our control, we cannot guarantee anything but the quality of the products it self. The information in this product data sheet is liable for modification from time to time in the light of experience and our policy of continuous product development, and without further notice.

ISSUED: January 2010