

Chlorinated Rubber

MIL-R-60671

22 May 1967

Superseding

FED-1657

14 July 1953

Requirements

Requirements	Grade 10		Grade 20	
	Minimum	Maximum	Minimum	Maximum
Chlorine Content	60%	---	60%	---
Specific Volume	1000 cm ³ / lb. min	---	1000 cm ³ / lb. min	---
Specific Gravity	1.30 min	---	1.30 min	---
Color	White-cream white	---	White-cream white	---
Viscosity	8	12	15	23
Granulation, percent:				
Through 20 mesh sieve	50%	---	50%	---
Through 60 mesh sieve	40%	---	40%	---
Through 100 mesh sieve	20%	---	20%	---