

Technical Data Sheet —

ALL ALLOYS NCP-89

WORLDWIDE TECHNOLOGY FEDERATION INC.

(For exterior or interior use)

NCP-89 is a high performance • single component • ambient air cure • Hydrophobic product creates a covalent bond to the substrate creating an intrinsic bond to Marble & Granite. an inert material when cured • will not contaminate nearby environments or food

has extreme hydrophobic properties making it an ideal water repellant surface coating

“odor free” once the coating has cured • produces a “High-Quality Gloss Finish”

has extreme UV resistance • and chemical resistance • soaks in – not just on the surface

Properties:

- Color _____ Clear
- Viscosity _____ 16-18 sec. #2 Zahn
- Percent of Solids _____ 28
- Odor (liquid) _____ Slight Solvent
- Odor (cured) _____ None
- V.O.C. _____ Exempt per CFR 51.1 / regulation 8
- RoHS _____ Compliant
- REACH _____ Compliant
- Halogens _____ None
- Thermal Stability (cured) _____ 1200°F + (648.8°C)
- Conical Bond (1/8 inch mandrel) _____ Passed (ASTM D522-93a)
- Cross cut adhesion _____ 5B (ASTM D3359)
- Coefficient of Friction _____ 0.03μ (ASTM D2047)
- Specific Gravity _____ 0.889 (ASTM D891-09)
- Pencil Hardness _____ 8h (ASTM D3363)
- Average applied dry film thickness _____ 2 to 5 microns
- Estimated Coverage Rate(@ 3 microns) _____ 3,800 sq./ft. per gallon**
(** will vary depending on Surface type)
- Transfer to surrounding material _____ Zero (0) transfer of contaminants
- Dry to Touch (time @ambient) _____ 15 – 25 minutes* (average)
(*a warm airflow will reduce time required to reach “Dry to the Touch”)
- Ambient cure (full properties) _____ 5 days

Manufacturer is not responsible for the use and application of this material. It is up to the end user determine the suitability of this product for their own application. It is the belief that the contents of this document we- accurate at the time of printing. No warranty is written or implied regarding application and use.