

**BIRLA INSTITUTE OF TECHNOLOGY AND
SCIENCES, PILANI
REPORT**

SECOND SEMESTER 2021-22



**Modification of g-C₃N₄ materials for use as
catalyst**

DATE: 26/05/22

SUPERVISOR:
Dr. Bibhas Ranjan Sir
Department of Chemistry

SUBMITTED BY:
Riddhi Arora
2018B2PS1169P

INDEX:

TOPIC	PAGE No.
ABSTRACT	2
INTRODUCTION	3
SCHEMATIC REACTION MECHANISM OF CARBON NITRIDE PHOTO-CATALYZED HYDROGEN EVOLUTION	4
PREPARATION OF g-C ₃ N ₄ -NHNH(CS ₂ Ni)	5
¹ H MAS (magic angle spinning) NMR	6
Powder-XRD of g-C ₃ N ₄ and g-C ₃ N ₄ (NHNHCS ₂ Ni)	8
TIME VS AMOUNT OF HYDROGEN GAS EVOLVED GRAPH	9
CONCLUSIONS	10
REFERENCES	11

ABSTRACT

By modifying the surface of graphite Carbon Nitride with Hydrazine, it allows connection of other function groups and ligands easily. The general method for noble-metal free h₂ gas evolution Graphite carbon nitride catalyst with stable hydrogen evolution is also mentioned. With 0.2 wt% nickel on the modified Graphite carbon nitride leads to 40% hydrogen evolution and more efficiency of 3 wt% Pt deposited on the g-C₃N₄ surface.


INTRODUCTION

The Polymeric carbon Nitride has gained much attention due to its application in Photocatalytic hydrogen evolution. The hydrogen evolution can be improved with modifying graphite carbon Nitrite's surface with noble metal or by doping the C₃N₄ with other building metals.

Few advantages are that the material can be produced using low cost starting materials, with that, it is non-toxic in nature, sustainable and eco-friendly.

The presence of strong C-N bonds, the material is ensured to have good thermal and chemical stability.


All these merits make it an ideal material for the application in hydrogen evolution as well as environmental pollutant degradation.



YinChen et al

Chemical Engineering Journal; Volume 286

SCHEMATIC REACTION MECHANISM OF CARBON NITRIDE PHOTO-CATALYSED HYDROGEN EVOLUTION



YinChen et al

Chemical Engineering Journal

Volume 286

Initiation: The g-C₃N₄ molecule absorbs photon energy equivalent to a minimum or more amount of band gap and thus produces an electron. The electron goes to the platinum nanoparticle trapped on the surface of the g-C₃N₄ molecule. This will initiate the charge separation due to lower work function which acts as a hydrogen electrolysis active centre.

The presence of heterogeneous catalyst gets the activity from the scarce locations on the surface; thus, it becomes difficult to regulate and understand how the active species like platinum nanoparticles react with the g-C₃N₄. Because of this it becomes difficult to improve the catalysis performance of g-C₃N₄.

PREPARATION OF g-C₃N₄-NHNH(CS₂Ni)

In this work, we have altered the surface of g-C₃N₄ with hydrazine and introduced the highly reactive NHNH₂ group; this later can be easily converted to CH₂NS₂- group after reacting with Carbon disulphide. Noble metal free hydrogen evolution catalysts can be obtained when the CH₂NS₂- group is coordinated to Ni²⁺.



YinChen et al

Chemical Engineering Journal


Volume 286

Compound 1 g-C₃N₄-NHNH₂


Compound 2 g-C₃N₄-NHNH(CS₂Na)

Compound 3 g-C₃N₄-NHNH(CS₂Ni)


^1H MAS (magic angle spinning) NMR



For the raw g-C₃N₄, ^1H MAS NMR showed a peak around 9.0 ppm due to the presence of NH₂ and NH groups.



After the reaction with CS₂, the intensity of the peak for the NHH₂ group decreased indicating most of the diazinyll group were consumed in the making of g-C₃N₄-NHHH(CS₂Na)




We know that the diazanyl group reacts with NaNO_2 to make the Triazo group, we found the peak at 4.2 ppm for $\text{g-C}_3\text{N}_4\text{-NHNH}_2$ **disappeared after reaction with excessive NaNO_2** at room temperature in ethanol for 15 min.

YinChen et al

Chemical Engineering Journal

Volume 286

Powder-XRD of g-C₃N₄ and g-C₃N₄ (NHNHCS₂Ni)




YinChen et al

Chemical Engineering Journal

Volume 286

- The above Powder-XRD of g-C₃N₄ and g-C₃N₄ (NHNHCS₂Ni) showed that there is no difference between their patterns.
- This also proves that the structure of graphite carbon nitride didn't change after a three steps reaction.

TIME VS AMOUNT OF HYDROGEN GAS EVOLVED GRAPH



YinChen et al

Chemical Engineering Journal

Volume 286

Curve a) It is a curve of time required for the evolution of water using 3 wt.% Pt deposited g-C₃N₄

Curve b) the time required for hydrogen evolution with g-C₃N₄-NHNH(CS₂Ni)

This proves that g-C₃N₄-NHNH(CS₂Ni) functions as a stable photocatalyst for visible-light-driven H₂ production.

Conclusions

In this project, we mentioned very simple ways of activating the surface of graphite carbon nitride which are comparatively cheap and easy g-C₃N₄ hydrogen evolution catalysts.

By treating the surface of g-C₃N₄ with noble metals. By adding diazanyl groups in g-C₃N₄, it becomes possible to introduce other functional groups or ligands to the compound. After reacting with carbon disulphide, the dithiocarbonate ligand is introduced into the graphite carbon nitride, which leads to the production of noble metal free hydrogen evolution catalyst after reacting with Nickel cation.

These results indicate that the molecular level catalyst designed strategy can work as H₂ evolution based on Graphite Carbon nitride, the surface catalysis active molecule can successfully replace the traditional co-catalyst nanoparticle. Because of this higher molecular catalysis efficiency was achieved.

REFERENCES

- High Efficiency Photocatalytic Water Splitting Using 2D α -Fe₂O₃/g-C₃N₄ Z-Scheme Catalysts by Xiaojie She et al First published: 08 May 2017
- Surface modification of g-C₃N₄ by hydrazine: Simple way for noble-metal free hydrogen evolution catalysts YinChen et al; Chemical Engineering Journal; Volume 286

Thank you