

BARIUM CHROMATE
MIL-B-550A
25 September 1958
Superseding
JAN-B-550
15 January 1948

Requirements

Beguirenens				
	Grade A		Grade B	
Requirements	Minimum	Maximum	Minimum	Maximum
Volatile matter, percent		0.10		0.20
Barium Chromate, percent	98.5		99.0	
Chlorides, (as CI), percent		0.05		0.05
Water Soluble matter, percent		0.05		0.08
Moisture reabsorption, percent				0.20
Apparent density, (gm/ml)	0.35	0.50	0.35	0.76
Granulation, percent:				
Through 100 mesh sieve			100.0	
Through 200 mesh sieve			98.0	
Through 325 mesh sieve	100			
Average Particle diameter (microns)		2		-3.5

On the web at: <a href="www.micronmetals.com">www.micronmetals.com</a> email: info@micronmetals.com