

# FOXSEALER WB (OD-101)

## Water Based Sealer Primer

<b>DESCRIPTION</b>	Water thinnable sealer based on acrylic dispersion.	
<b>CHARACTERISTIC</b>	<p>Level the absorption of untreated substrates.</p> <p>Unsaponifiable.</p> <p>Recoat able with dispersion an alkyd resin paints.</p> <p>Wall paper application on top possible.</p> <p>Fixes powdering or chalking old layer on porous substrate.</p> <p>Prevents discolouring.</p> <p>Good alkali resistance properties.</p>	
<b>RECOMMENDED USE</b>	As a sealing agents for interior and exterior wall coating.	
<b>SPECIFICATION DATA AT 20°C</b>	<p>Gloss</p> <p>Colours</p> <p>Specific gravity</p> <p>Coverage theoretical</p> <p>Touch dry</p> <p>Painting interval</p> <p>Shelf life</p>	<p>Flat</p> <p>Milky ; driers colourless</p> <p>1.0 ± 0.1 kg/litre</p> <p>8 – 10 m<sup>2</sup>/litre, depending on the absorption of the surface.</p> <p>2 hours</p> <p>6 hours</p> <p>9 month (cool and dry place)</p>
<b>SURFACE PREPARATION</b>	Substrate must be free of any contamination, Substrate containing lime and cements should be properly dried, hard and fully reacted.	
<b>INSTRUCTION FOR USE</b>	<p>Stir well before use of paint.</p> <p>Method of application</p> <p>Thinner</p> <p>Volume of thinner</p>	<p>Brush / roller</p> <p>Tap water</p> <p>0–5%</p>
<b>SAFETY PRECAUTION</b>	<p>Avoid contact with the skin and eyes.</p> <p>Wear suitable protective clothing such as overalls, goggles, dust mask and gloves.</p> <p>Ensure that there is adequate ventilation in the area where the product is being applied.</p> <p>Do not breathe the vapour or spray.</p>	
<b>HEALTH AND SAFETY</b>	For detailed information on the health and safety hazards and precaution for use of this product, please see the <b>MATERIAL SAFETY DATA SHEET</b> .	
<b>PACKING SIZE AND STORAGE</b>	<p>Packing size</p> <p>Storage</p>	<p>5 and 20 litres.</p> <p>The product must be storage in accordance with national regulation. Preferred storage conditions are the keep the containers in the dry space provided with adequate ventilation. The container should be sealed tightly.</p>